



# BIODAM

## Technical Data Sheet

### Typical Properties

- |                          |               |
|--------------------------|---------------|
| ▪ 100% Modulus (MPa)     | 0.60+/- 0.20  |
| ▪ 200% Modulus (MPa)     | 1.0 0+/- 0.20 |
| ▪ 300% Modulus (MPa)     | 1.40 +/- 0.40 |
| ▪ Elongation (%)         | 850 +/- 200   |
| ▪ Tensile Strength (MPa) | Over 20       |
| ▪ Tear Resistance (N/mm) | Over 70       |

### THICKNESS

Thin Gauge 0.006"  
Medium gauge 0.008"  
Heavy Gauge 0.010"

Available in 5" x 5" or 6" x 6" squares

### COLOURS

Green  
Blue

### SAFETY INFORMATION

#### **Composition:**

Natural rubber plus minimum hazardous rubber processing chemicals and pigments.

#### **Health Hazard:**

This product has been made by removal of unreacted chemicals and

proteins to the permitted level by excessive hot water leaching and is generally considered safe for use. People who are allergic to natural latex should avoid the product. Test the product for allergies before first use. If any allergic reactions occur seek medical advice.

**Four D Rubber Co. Ltd.**  
Slack Lane, Heanor Gate Industrial Estate  
Heanor, Derbyshire, DE75 7GX, England

**Tel: +44 (0) 1773 763134**  
**Email: [info@fourdrubber.com](mailto:info@fourdrubber.com)**  
**Web: [www.fourdrubber.com](http://www.fourdrubber.com)**